

Product Description

Lyten's 3D Graphene™ Epoxy Adhesive is a two-component toughened paste adhesive with high tensile lap shear strength.

Features

High temperature service life

Formulated w/ 3D Graphene

Separate two-part system for ease of use & mix

Uncured Properties	Part A	Part B	Mixed
Color	Off White	Black	Black
Viscosity ⁽¹⁾	56 Pa·S	15 Pa·S	20 Pa·S
Density	1.20 g/mL	1.03 g/mL	1.15 g/mL
Shelf Life at:			
<77°F/25°C	6 months	6 months	

Handling

Mixing – Combine Part A and Part B according to the mix ratio shown below before applying to the parts. Complete mixing is required for optimal results. The temperature of both components should be equilibrated to room temperature (77 °F or 25 °C), although not required.

Mix Ratio	Part A	Part B
By Weight	100	43
By Volume	2	1

Note: Wt. ratio is recommended for structural applications.

Pot Life⁽²⁾ – 80 minutes at 77 °F (25 °C)

Application

Mixing – It is important to mix Part A and Part B thoroughly at the correct ratio. Do not mix over 450 grams, as heat buildup can occur, and the mixed adhesive may lead to decomposition. Toxic fumes can be generated and cause personal injury. Mixing at smaller quantities will minimize the heat buildup.

Applying – The surface to which adhesive is applied should be clean and dry. The bonded parts should be held in contact until the adhesive is set to a handling strength, which can be achieved in 24 hours at 77 °F or 25 °C. After that, any tooling or pressure used to support the bonded parts may be removed. Until the full bond strength is achieved, load application should be small.

Curing – For optimal bond strength, cure the adhesive for 1 hour at 176 °F (80 °C); alternatively, a 1-hour cure at 150 °F (65 °C) is acceptable.

Clean-up – To clean up excess uncured adhesive, use denatured alcohol, acetone, MEK, or any industrial solvents. For safe and proper use of solvents, please refer to the supplier's information.

Bond Strength Performance

Tensile lap shear strength – tested per ASTM D1002. Adherends are 2024-T3 AlClad aluminum at 0.063 inch (0.51mm) thickness treated with phosphoric acid anodize per ASTM D3933.

Adhesive Cure Parameter	Test Temperature		Typical Results	
	°F	°C	psi	MPa
1 h at 150 °F (65 °C)	68	20	6,060	41.8
	194	90	3,030	20.9
1 h at 176 °F (80 °C)	68	20	6,270	43.2
	194	90	2,370	16.3
	230	110	1,075	7.4

Tensile lap shear strength – tested per ASTM D5868. Adherends are carbon fiber reinforced epoxy.

Adhesive Cure Parameter	Test Temperature		Typical Results*	
	°F	°C	psi	MPa
1 h at 150 °F (65 °C)	68	20	2,710	18.7
	194	90	2,350	16.2
1 h at 176 °F (80 °C)	68	20	3,450	23.8
	194	90	2,640	18.2
	230	110	1,600	11.0

*Substrate failure

Floating Roller Peel Strength – tested per ASTM D3167. Adherends are 2024-T3AlClad peeling skin at 0.020 inch (0.51 mm) thickness and backing skin at 0.063 inch (1.6 mm) thickness aluminum treated with phosphoric acid anodize per ASTM D2922 and primed with BR-127.

Adhesive Cure Parameter	Test Temperature		Typical Results	
	°F	°C	lb/in	N/25mm
1 h at 150 °F (65 °C)	68	20	28	123

Additional Testing Information

⁽¹⁾ Viscosity was measured at 25 °C (77 °F) at 2.1 rad/sec.

⁽²⁾ Pot life (working life) was measured according to ISO 10346 under the following conditions:

- a. Measuring system: plate-plate system with a 25mm parallel plate geometry
- b. Shear conditions: at the shear rate of 1 s-1 with continuous shear with 1 s/pt sampling interval
- c. Conditioning temperature: 25 °C (77 °F)
- d. Mix ratio: 100:43 (A:B)
- e. Total amount of adhesive mixed: 7 g
- f. Amount of adhesive transferred into the measuring system: 1.5 g

Legal

Lyten, the Lyten logo, Lyten 3D Graphene, etc. are trademarks of Lyten, unless indicated otherwise. Lyten makes no warranty, representation, or guarantee regarding the information contained herein or the suitability of its products and services for any particular purpose, nor does Lyten assume any liability whatsoever arising out of the application or use of any product. It is the user's responsibility to independently determine suitability of any products and to test and verify the same. The information provided by Lyten hereunder is provided "as is." Lyten does not grant, explicitly or implicitly, to any party any patent rights, licenses, or any other IP rights, whether with regard to such information itself or anything described by such information. Information provided in this document is proprietary to Lyten, and Lyten reserves the right to make any changes to the information in this document or to any products and services at any time without notice.